

MAXICLENE



DESCRIPTION

MAXICLENE is a mixture of very strong acids in solution which are highly effective for removing mortar smudges and red rust and white calcium stains from clay brickwork.

NOTE: Only persons that have a license from the Health Department are able to purchase this product.

DIRECTIONS

RUST STAINS (RED OR WHITE) MORTAR SMUDGES

Trial dilutions of MAXICLENE up to 10 parts with water on the affected clay brick or ceramic substrate. 1 litre of MAXICLENE makes up to 10 litres of an appropriate dilution. For a more economical dilution, MAXICLENE can be diluted 1 : 1 with HCl 30%*m/m*. Hard deposits are usually removed with undiluted MAXICLENE.

Treat stained bricks or ceramic substrates singularly or one-quarter of a square metre at a time. Work on a dry substrate and up a wall. Apply MAXICLENE solution to dry substrate and scrub it around for a short while. While the substrate face is still wet, immediately wash with water, scrubbing as you wash. Repeat this process on the next portion of the walls, either up or along the substrate.

Neutralise treated area with NEUTRA. After 15 minutes of contact with the diluted NEUTRA solution, rinse the treated area with water.

To check the neutralising with NEUTRA solution, use litmus paper (red paper turns blue) or pH paper. Either should have a reading of Ph 7 - 8.

CLEAN UP

Clean up is done on site with water and neutralise with NEUTRA. Collect and dispose of the

neutralised waste in accord with the relevant environmental protection laws. Neutralisation and correct disposal is very important because MAXICLENE will vaporise, and attack metal fittings and fixtures. This is especially damaging inside a house, for example, on fridges, bathroom taps or cupboard fittings etc.

PRECAUTIONS/FIRST AID

Wear coveralls, eye protection, acid resistant gloves and safety boots.

HYDROFLUORIC ACID attacks all of the body: eyes, bones and fingernails. It is an extremely dangerous acid, but is required because there is no alternative chemical which has similar activity and efficiency of stain deposit removal that can replace it for this purpose of use.

The acids in MAXICLENE attacks all metals, anodised aluminium, concrete, glass, timber, paint, especially if left for a long period. Short term placement with removal soon after usually does not show any defect. Thus, these items must be masked from MAXICLENE when in use and when it is being removed. Always neutralise with NEUTRA.

First aid for different exposures is listed below:

INHALED: Avoid breathing vapour or spray mists.

Wear a face mask with absorbent cartridges.

SWALLOWED: Drink water or milk. Do not induce vomiting.

SKIN: Remove any contaminated clothing. Wash off with water followed by soap and water. Rub calcium gluconate gel over areas where contact has occurred.

EYES: Hold the eyelids open and wash with copious quantities of water for 15 minutes.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 1 of 2
ISSUE: JULY 2011
REF: MXCL

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.

MAXICLENE



SEEK IMMEDIATE MEDICAL ADVICE IN ALL CASE.

STORAGE

Store MAXICLENE in a cool area, between 5 - 30°C under cover and away from any other chemicals, foodstuffs or items.

PACK SIZES

MAXICLENE is sold in packs of 20 litres.

TRANSPORT

UN No 1790 : CLASS 8 : SUB CLASS 6.1(a) :
HAZCHEM 2XE : PACKAGING GROUP II
PLASTIC CONTAINERS : IERG. No. 40.
SAFETY PHRASES 1, 3, 4, 5, 8, 29, 35 : RISK
PHRASES 1, 17, 93

MAXICLENE is classified as a hazardous good for transport by Worksafe Australia.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0418 956 860

IDENTIFICATION
PAGE 2 of 2
ISSUE: JULY 2011
REF: MXCL

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.