

# TUFSEAL



## DESCRIPTION

TUFSEAL is a waterborne fine-particle pure acrylic resin. TUFSEAL is an excellent roof and wall coating.

## FEATURES

TUFSEAL exhibits excellent film properties with clarity, gloss, durability and resistance to blocking, soiling and resistance to algae and fungi.

## USES

- \*Sealing brick walls internally to suppress dust.
- \*Sealer for porous or dense substrates, either clear or coloured before painting or texture coating.
- \*Seal and finish coating for roof tiles.

## COVERAGE

Average coverage per coat of TUFSEAL as supplied is 6-8 m<sup>2</sup>/litre/coat.

## PREPARATION

- The surfaces TUFSEAL is to be placed on should be sound and free of dust, oil, mould. Fungi, algae and laitence.
- Old paint should be firmly bonded to the surface, otherwise it should be removed if loose or the under-surface is deteriorated. Old painted surfaces should be primed with ELASTATAK.
- Tile or steel rooves should be waterblasted and let dry before application of TUFSEAL.

## DIRECTIONS

**SEALING BRICK WALLS:** Dilute TUFSEAL CLEAR 1 : 1 with water. Apply one coat of this dilution at 6-8m<sup>2</sup>/litre. If walls are highly porous, apply two coats, 2 – 4 hours apart @25°C. Allow to dry for 4 hours @25°C.

If required, the dried TUFSEAL can be overcoated with another coating product, e.g. FLEXITEX, TUFSEAL COLOURED, FLEXIDECK or left as a clear for internal use.

**ROOF COATING:** Dilute TUFSEAL CLEAR 1 : 1 with water. Apply one coat of this dilution at 6-8m<sup>2</sup>/litre. Two coats are necessary for very porous tiles. Allow to dry for 4 hours @25°C

Follow with TUFSEAL COLOURED at a rate of 6-8m<sup>2</sup>/litre/coat. Two coats of TUFSEAL COLOURED are necessary. Allow 2-4 hours between coats @25°C.

Do not apply if humidity is above 75% or if rain or inclement weather is expected within 72 hours. TUFSEAL should not be applied if temperature is below 10°C or above 35°C.

## STORAGE

TUFSEAL should be stored in a covered, cool area between 5-30°C. The lid should be replaced after decanting or use.

## CLEAN UP

Clean tools with water immediately after use. If TUFSEAL sets as a film, remove with MARCMOVE or WIZ STRIP.

## PACK SIZES

TUFSEAL is sold in packs of 20 and 200 litres.

## TRANSPORT

TUFSEAL is not a hazardous good as defined by WorkSafe Australia.

FACTORY  
16 GOONGARRIE STREET  
BAYSWATER WA 6053  
AUSTRALIA

POSTAL  
PO BOX 385  
BAYSWATER WA 6933  
AUSTRALIA

TELEPHONE  
TEL. (08) 9378 2022  
FAX. (08) 9377 2575  
MOB. 0418 956 860

IDENTIFICATION  
PAGE 1 of 1  
ISSUE: JULY 2011  
REF: TFSL

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. M.S.D.S. is available.