

HYPOBOND



DESCRIPTION

HYPOBOND is a waterborne fine particle size pure acrylic adhesive emulsion in an emulsified format. When set as an adhesive film joining delaminated substrates, the bond is strong with a degree of flexibility.

FEATURES

HYPOBOND is easy to inject through fine holes (1.6mm) using size 16-18 hypodermic needle attached to an automatic refillable hand applied syringe or a variable air-controlled compressor pump if large scale injection is required.

APPLICATION

HYPOBOND is designed to be injected by low pressure to form a bonding adhesive layer when set between delaminated substrates.

- Bonding drummy ceramic tiles.
- Bonding drummy cement/sand render.
- Bonding delaminated parquetry timber flooring.
- Bonding loose joints in timber frames, e.g. wooden windows.
- Bonding drummy float/set coatings, e.g. internal plaster.

PRECAUTIONS

Coverage of **HYPOBOND** is difficult to specify a fixed amount per use. Quantity of **HYPOBOND** used for a particular application varies as some applications require little **HYPOBOND** and others will use more. This is because the quantity of **HYPOBOND** necessary to fill gaps, hollows and laminations between substrates vary.

DIRECTIONS

Use back of metal soup spoon or coin to tap surface of tiles to find drummy areas. Use electric drill with a 1.6mm drill bit to bore holes in selected points around surface that is drummy. For tiles, holes are usually drilled at the corners of the tile, in

the grout lines. When all holes are drilled, use a vacuum cleaner to remove mortar powder and dust from the drilling. Using **HYPOBOND** syringe, start to flow the **HYPOBOND** liquid through the clear tubing towards the tip. Make sure the tip of the extrusion device is clear of obstruction by passing a small portion of the **HYPOBOND** liquid through the tip.

If the tip is clear of obstructions, place it in a hole of the surface and start injecting the **HYPOBOND** liquid underneath the surface. If the hole has gone through to a drummy section, the liquid will flow easily. If the hole didn't make it thought to a drummy section, the liquid will be very hard to extrude, and another hole should be drilled in the near vicinity. A hole has been completely saturated when the **HYPOBOND** liquid starts to come out of adjoining holes. It is then time to move onto the next hole. A toothpick can be used to plug saturated holes to prevent runs.

When all holes have been done, use a dry rag to clean any excess **HYPOBOND** off the surface. Mix the grout additive in a plastic cup and with a pop stick, fill the existing drill holes with the paste using a toothpick or similar object. When this task is completed, wipe off any excess with a dry rag. 24 hours after the injection and grouting process has been completed, wash the section (or the whole floor) of tiles that were attended to, to remove any grease or fat left the day before. For timber, plaster or renders, use appropriate filling compounds to fill holes.

STORAGE

HYPOBOND should be stored fully sealed in a covered, cool area in a temperature range of 10-30°C. The lid or cover for the container should be replaced after each decanting of the contents.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0408 940 669

IDENTIFICATION
PAGE 1 of 2
ISSUE: JULY 2011
REF: HYBD

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)
This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. S.D.S. is available.

HYPOBOND



CLEAN UP

Clean all tools and substrates with spills on them with a water dampened rag while the **HYPOBOND** is still liquid. If the **HYPOBOND** has set as a film, remove the set film with **MARCMOVE** or **WIZSTRIP**.

PACK SIZES

HYPOBOND is sold in packs of 1, 5, 10 and 20 litres.

TRANSPORT

HYPOBOND is not a dangerous or hazardous good as defined by Safe Work Australia.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0408 940 669

IDENTIFICATION
PAGE 2 of 2
ISSUE: JULY 2011
REF: HYBD

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)

This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. S.D.S. is available.