

CALSEAL



DESCRIPTION

CALSEAL is a waterborne pure acrylic resin, reinforced with fine waxes, which upon drying forms a semi-gloss clear film with exceptional toughness, water and dirt resistance necessary in external environments.

FEATURES

CALSEAL exhibits excellent film properties with clarity, durability and resistance to marring, UV, water and soiling.

USES

- Coloured seal finish for high build coatings.
- Two coat coloured finish for exterior renders.
- Clears for sealing porous substrates internally such as natural limestone walls.

PREPARATION

FOR ALL APPLICATIONS: The surface that **CALSEAL** is to be applied to should be firm and free of dust, oil, laitence, mould, algae and fungi.

APPLICATION RATES

SEAL COAT FOR HIGH BUILD COATINGS:

Apply one coat of **CALSEAL** at 8-10m²/litre.

TWO COAT FINISH FOR CEMENT RENDERS:

Apply one coat of **GENPRIME** at 8-10m²/litre. Allow to dry for 2-4 hours at 25°C.

Apply two coats of **CALSEAL** at 8-10m²/litre/coat. Allow first coat to dry before applying second coat. A minimum of 4 hours at 25 degrees Celsius is recommended between coats.

SEAL COAT FOR PROUS SUBSTRATES:

Dilute **CALSEAL** 50% with water, stir well. Apply two coats at 6-8m²/litre/coat. Allow first coat to dry before applying second coat. A minimum of 4 hours at 25 degrees Celsius is recommended between coats. Recommended for internal limestone walls.

For external limestone walls, refer to **CALICONE** data sheet.

CLEAN UP

Clean up with water when **CALSEAL** is wet. If it is a dry film, use **MARCMOVE** or toluene.

STORAGE

Store **CALSEAL** in sealed containers under cover in a cool area away from foodstuffs.

PACK SIZES

CALSEAL is sold in packs of 5, 10, 20 and 200 litres.

TRANSPORT

CALSEAL is not a hazardous good as defined by Safe Work Australia.

FACTORY
16 GOONGARRIE STREET
BAYSWATER WA 6053
AUSTRALIA

POSTAL
PO BOX 385
BAYSWATER WA 6933
AUSTRALIA

TELEPHONE
TEL. (08) 9378 2022
FAX. (08) 9377 2575
MOB. 0408 940 669

IDENTIFICATION
PAGE 1 of 1
ISSUE: JULY 2011
REF: CLSL

QUINDALUP HOLDINGS PTY LTD (A.C.N. 009 026 386) AS TRUSTEE FOR CALMARC FAMILY TRUST (ABN 18 340 289 669)
This information is offered solely for the customer and/or specifier for their consideration, investigation and verification. The suggestions mentioned herein should be fully assessed prior to application. No warranty or implied liability is given for any recommendations, advice, suggestions made by Calmarc Chemicals or representatives, agents or distributors for the conditions of use and labour for the products which are beyond our control. Catalogue or specification contents may change from time to time without notice. S.D.S. is available.